



UNIVERSAL BEAMS




Designation	Mass per Metre	Depth of Section	Width of Section	Thickness Web	Thickness Flange	Root Radius	Depth between fillets
		h	b	s	f	r	d
	kg/m	mm	mm	mm	mm	mm	mm
127 x 76	13	127	76	4	7.6	7.6	96.6
152 x 89	16	152.4	88.7	4.5	7.7	7.6	121.8
178 x 102	19	177.8	101.2	4.8	7.9	7.6	146.8
203 x 102	23	203.2	101.8	5.4	9.3	7.6	169.4
203 x 133	25	203.2	133.2	5.7	7.8	7.6	172.4
	30	206.8	133.9	6.4	9.6	7.6	172.4
254 x 102	22	254	101.6	5.7	6.8	7.6	225.2
	25	257.2	101.9	6	8.4	7.6	225.2
	28	260.4	102.2	6.3	10	7.6	225.2
254 x 146	31	251.4	146.1	6	8.6	7.6	219
	37	256	146.4	6.3	10.9	7.6	219
	43	259.6	147.3	7.2	12.9	7.6	219
305 x 102	25	305.1	101.6	5.8	7	7.6	275.9
	28	308.7	101.8	6	8.8	7.6	275.9
	33	312.7	102.4	6.6	10.8	7.6	275.9
305 x 127	37	304.4	123.3	7.1	10.7	8.9	265.2
	42	307.2	124.3	8	12.1	8.9	265.2
	48	311	125.3	9	14	8.9	265.2
305 x 165	40	303.4	165	6	10.2	8.9	265.2
	46	306.6	165.7	6.7	11.8	8.9	265.2
	54	310.4	166.9	7.9	13.7	8.9	265.2

UNIVERSAL BEAMS



Designation	Mass per Metre	Depth of Section	Width of Section	Thickness Web	Thickness Flange	Root Radius	Depth between fillets
		h	b	s	f	r	d
	kg/m	mm	mm	mm	mm	mm	mm
356 x 127	33	349	125.4	6	8.5	10.2	311.6
	39	353.4	126	6.6	10.7	10.2	311.6
356 x 171	45	351.4	171.1	7	9.7	10.2	311.6
	51	355	171.5	7.4	11.5	10.2	311.6
	57	358	172.2	8.1	13	10.2	311.6
	67	363.4	173.2	9.1	15.7	10.2	311.6
406 x 140	39	398	141.8	6.4	8.6	10.2	360.4
	46	403.2	142.2	6.8	11.2	102.2	360.4
406 x 178	54	402.6	177.7	7.7	10.9	102.2	360.4
	60	406.4	177.9	7.9	12.8	10.2	360.4
	67	409.4	178.8	8.8	14.3	10.2	360.4
	74	412.8	179.5	9.5	16.0	10.2	360.4
457 x 152	52	449.8	152.4	7.6	10.9	10.2	407.6
	60	454.6	152.9	8.1	13.3	10.2	407.6
	67	458.0	153.8	9.0	15.0	10.2	407.6
	74	462.0	154.4	9.6	17.0	10.2	407.6
	82	465.8	155.3	10.5	18.9	10.2	407.6
457 x 191	67	453.4	189.9	8.5	12.7	10.2	407.6
	74	457.0	190.4	9.0	14.5	10.2	407.6
	82	460.0	191.3	9.9	16.0	10.2	407.6
	89	463.4	191.9	10.5	17.7	10.2	407.6
	98	467.2	192.8	11.4	19.6	10.2	407.6

UNIVERSAL BEAMS



Designation	Mass per Metre	Depth of Section	Width of Section	Thickness Web	Thickness Flange	Root Radius	Depth between fillets
		h	b	s	f	r	d
	kg/m	mm	mm	mm	mm	mm	mm
533 x 210	82	528.3	208.8	9.6	13.2	12.7	476.5
	92	533.1	209.3	10.1	15.6	12.7	476.5
	101	536.7	210	10.8	17.4	12.7	476.5
	109	539.5	210.8	11.6	18.8	12.7	476.5
	122	544.5	211.9	12.7	21.3	12.7	476.5
610 x 229	101	602.6	227.6	10.5	14.8	12.7	547.6
	113	607.6	228.2	11.1	17.3	12.7	547.6
	125	612.2	229	11.9	19.6	12.7	547.6
	140	617.2	230.2	13.1	22.1	12.7	547.6
610 X 305	149	612.4	304.8	11.8	19.7	16.5	540
	179	620.2	307.1	14.1	23.6	16.5	540
	238	635.8	311.4	18.4	31.4	16.5	540
686 x 254	125	677.9	253	11.7	16.2	15.2	615.1
	140	683.5	253.7	12.4	19	15.2	615.1
	152	687.5	254.5	13.2	21	15.2	615.1
	170	692.9	255.8	14.5	23.7	15.2	615.1
762 x 267	134	750	264.4	12	15.5	16.5	686
	147	754	265.2	12.8	17.5	16.5	686
	173	762.2	266.7	14.3	21.6	16.5	686
	197	769.8	268	15.6	25.4	16.5	686
838 x 292	176	834.9	291.7	14	18.8	17.8	761.7
	194	840.7	292.4	14.7	21.7	17.8	761.7
	226	850.9	293.8	16.1	26.8	17.8	761.7